(C) approximately from 5 to 20% , relative to the total weight of the polymers (A) and (B), of a monomeric or polymeric plasticizer.

7. (Amended) A shaped article consisting totally or partially of a composition comprising a PVDF homopolymer and at least one fluorocopolymer, where in the composition comprises, by weight,

B1

(A) approximately from 60 to 80 % of at least one PVDF homopolymer;

(B) approximately from 20 to 40% of at least one thermoplastic copolymer of vinylidene fluoride (VF_2) and of at least one other fluoromonomer, present in this copolymer in weight proportions of approximately 5 to 25%,

(C) approximately from 5 to 20% , relative to the total weight of the polymers (A) and (B), of a monomeric or polymeric plasticizer.

Please add Claims 8-15:

--8. The pipe of claim 6, in which the fluoromonomer is selected from the group consisting of hexafluoropropylene, chlorotrifluoroethylene and trifluoroethylene.

--9. The pipe of claim 6, in which the copolymer exhibits a melt index (MFI at 230°C and under 10 kg) lower than approximately 6g/10 min.

--10. The pipe of claim 6, in which the plasticizer includes dibutyl sebacate.

B2

--11. The pipe of claim 6, in which the plasticizer includes at least one polymeric polyester , with a molecular mass of approximately 1500 to 5000, wherein the polyester is formed of a diol and an acid selected from the group consisting of adipic acid, azelaic acid and sebacic acid. --

--12. The shaped article of claim 7, in which the fluoromonomer is selected from the group consisting of hexafluoropropylene, chlorotrifluoroethylene and trifluoroethylene.--

--13. The shaped article of claim 7, in which the copolymer exhibits a melt index (MFI at 230°C and under 10 kg) lower than approximately 6g/10 min.--

B2

--14. The shaped article of claim 7, in which the plasticizer includes dibutyl sebacate.--

--15. The shaped article of claim 7, in which the plasticizer includes at least one polymeric polyester , with a molecular mass of approximately 1500 to 5000, wherein the polyester is formed of a diol and an acid selected from the group consisting of adipic acid, azelaic acid and sebacic acid.--